



Laminating Adhesives Data Page

FOD # 0330

3M™ 467MP Roll Laminating Adhesive 468MP Roll Laminating Adhesive

Product Construction

	<u>Adhesive</u>	<u>Liner</u>
467MP	2.0 mils (50 microns) #200MP “Hi-Performance” Acrylic Adhesive	4.0 mils (100 microns) 58# Tan Polycoated Kraft Paper
468MP	5.0 mils (125 microns) #200MP “Hi-Performance” Acrylic Adhesive	4.0 mils (100 microns) 58# Tan Polycoated Kraft Paper

Features

- High performance solvent-free acrylic adhesive for exceptional environmental resistance and enhanced bond strength.
- Superior adhesive smoothness for improved clarity and reduced telegraphing through thin plastic facestocks.
- High cohesive strength for resistance to edge lifting and slippage.
- 2.0 mil 467MP is ideal for application to relatively smooth surfaces.
- 5.0 mil 468MP is ideal for application to a variety of rough or textured surfaces.
- Moisture stable liner resists curling or wrinkling in high humidity.
- 200MP Hi-Performance adhesive is initially repositionable, then builds to high ultimate bond strength.

Applications

- Long term bonding of nameplates and decorative trim to metal and high surface energy plastics in the automotive, appliance and electronic markets.
- Excellent adhesive for bonding metal and plastic nameplates in the aerospace, instrumentation and medical markets.
- Used for lamination to back printed polycarbonate or polyester graphic overlay materials in the automotive, electronics and membrane switch markets.
- Used for lamination of wood veneers and plastic laminates to cabinetry and furniture.
- Used in the assembly of membrane switches, including spacers for circuit separation graphic overlay for switch display and bonding the complete switch to the application surface.

Physical Properties

(Typical values – not for specification use)

ASTM D-3330 (modified)

90 degree peel, 12"/min.

(305 mm/min) 2 mil

aluminum

	Product	20 Min. Dwell	
		Oz./In. N/100 mm	
- Metal (Stainless Steel)	467MP	44	48
	468MP	59	64
- High Surface Energy Plastic (ABS)	467MP	40	44
	468MP	52	57

3M Test (90 degree peel,

12"/min. 305 mm/min.)

2 mil aluminum to

various surfaces

	Product	72 Hr. Dwell		Ultimate Bond	
		Oz./In. N/100 mm		Oz./In. N/100 mm	
- Metal (Stainless Steel)	467MP	82	90	113	124
	468MP	109	119	178	194
- High Surface Energy Plastic (ABS)	467MP	47	51	43	47
	468MP	61	67	58	63
- Low Surface Energy Plastic (Polypropylene)	Not Recommended				

Environmental Performance

The properties defined are based on the attachment of impervious faceplate materials (such as aluminum) to an aluminum test surface.

Bond Build-up:	The bond strength of #200MP "Hi-Performance" Acrylic Adhesive increases as a function of time and temperature.
Humidity Resistance:	High humidity has a minimal effect on adhesive performance. Bond strengths are generally higher after exposure for 7 days at 90 degrees F (32 degrees C) and 90% relative humidity.
U.V. Resistance:	When properly applied, nameplates and decorative trim parts are not adversely affected by outdoor exposure.
Water Resistance:	Immersion in water has no appreciable effect on the bond strength. After 100 hours in room temperature water the bond actually shows an increase in strength.
Temperature Cycling Resistance:	Bond strength generally increases after cycling four times through: 4 hours at 158 degrees F (70 degrees C) 4 hours at -20 degrees F (-29 degrees C) 16 hours at room temperature
Chemical Resistance:	When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including gasoline, oil, "Freon" TF, sodium chloride solution, mild acids and alkalis.
Low Service Temp:	-40 degrees F (-40 degrees C).
Heat Resistance:	The #200MP "Hi-Performance" adhesive is usable for short periods (minutes, hours) at temperatures up to 400 degrees F (204 degrees C) and for intermittent longer periods of time (days, weeks) up to 300 degrees F (149 degrees C).
Shelf Life:	Product retains its performance and properties for two years from date of manufacture if properly stored at room temperature conditions of 72 degrees F (22 degrees C) and 50% R.H. Storage in plastic bag is recommended.

Processing

Die-cutting:	Excellent die-cuttability. For easier processing lubricate dies with Laminoleum vanishing oil available from Metal Lubricants (708-333-8900).
Roll Laminating:	Excellent processability. A combination of metal and rubber rollers with moderate pressure is recommended.

Special Considerations/Application Tips

For maximum bond strength the surface should be thoroughly cleaned and dried. Typical cleaning solvents are heptane or isopropyl alcohol. Consult solvent manufacturer's Material Safety Data Sheet for proper handling and storage instructions.

Bond strength can also be improved with firm application pressure and moderate heat causing the adhesive to develop intimate contact with the bonding surface.

Ideal adhesive application temperature range is 70 degrees F to 100 degrees F (21 degrees C to 38 degrees C). Application is not recommended if surface temperature is below 50 degrees F (10 degrees C) because the adhesive becomes too firm to adhere readily. Once properly applied, low temperature holding is satisfactory. For more specific information contact our Customer Service and Sales Support "hot line" at 1-800-223-7427.

2/15/96

Terms and Conditions of Sale for products sold by 3M Identification and Converter Systems Division can be found in the ICSD Price Book and in other appropriate schedules.

Technical Data: All physical properties, statements, and recommendations are either based on tests we believe to be reliable or our experience, but they are not guaranteed. 3M recommends each user determine the suitability of the products for the intended use.

Warranty and Limited Remedy: THE FOLLOWING WARRANTY IS MADE IN LIEU OF ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE AND ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, A CUSTOM OR USAGE OF TRADE: 3M warrants its product will be free from all defects.

If a product is proved to be defective, then the exclusive remedy 3M's and seller's sole obligation shall be, at 3M's option, to replace the quantity of the product which is proved to be defective or to refund the purchase price.

Limitation of Liability: 3M and seller shall not be liable for direct, indirect, special, incidental or consequential damages based breach of warranty, breach of contract, negligence, strict liability or any other legal theory.

The foregoing Warranty and Limited Remedy and Limitation of Liability may be changed only by a written agreement signed by authorized officers of 3M and seller.

Scotch, ScotchMark, ScotchCap, and Stamark are trademarks of 3M.



Identification and Converter Systems Division

3M Center, Building 220-7W-03
St. Paul, MN 55144-1000
USA
1 800 223 7427
1 800 258 7511 FAX
e-mail idconvert@mmm.com

3M Canada Inc.

PO Box 5757
London, Ontario
Canada N6A 4TI
1 800 265 1840
519 452 6090 FAX
©3M 1996

3M Mexico, S.A. de C.V.

Apartado Postal 14-139
Mexico, D.F. 07070
Mexico
52 5 728 2289
52 5 728 2299 FAX

3M Puerto Rico, Inc.

Puerto Rico Industrial Park
PO Box 100
Carolina, PR 00986-0100
809 750 3000
809 750 3035 FAX